

Avg Results Of Fcml-1

YARN	10/1 Siro	16/1 warp	20/1 warp	30/1 warp	20/1 Hos	13/1 Soft.	20/1 Warp	36/1 Warp
YARN	Normal	Normal	Normal	Compact.	Normal	Compact.	Compact	Compact
COTTON	PAK	PAK	PAK	PAK	PAK	PAK	Viscose 44 mm	Viscose 44 mm
Actual Count	10.05	16.1	20.2	30.2	19.85	13.1	20.2	36.5
Count CV %	1.00	1.10	1.05	1.15	1.20	1.15	1.25	1.30
Strength	260	165	122	85	114	200	170	84
Stren. CV %	3.05	3.18	3.4	3.01	3.5	3.3	3.2	3.1
CLSP	2613	2657	2464	2567	2263	2620	3434	3066
RKM (UTJ-4)	18.66	18.98	17.60	18.34	16.16	18.71	24.53	21.90
U %	9.75	10.75	11.9	12.8	11.5	10.00	9.00	10.80
Thin -50 %	0	0	5	15	2	0	0	5
Thick +50 %	35	90	250	300	200	50	15	15
Neps +200 %	20	80	200	250	180	50	40	50
I P I	50-60	150-175	400-500	500-650	350-400	80-120	40-60	65-80
Hairiness	9.5	7.5	6.8	4.5	6.8	5.8	5.4	4.0
sh	1.9	1.5	1.5	1.1	1.5	1.3	1.3	1.0

40/1 Warp	42/1 Warp	20/1 PV
Compact	Compact	Normal
Viscose 44 mm	Viscose 44 mm	P.V 38mm
40.5	42.5	20.25
1.25	1.20	1.25
75	71	220
3.2	3.2	3.5
3038	3018	4455
21.70	21.55	31.82
10.50	10.60	9.40
5	5	0
20	25	3
50	50	5
65-80	75-85	5-10
3.4	3.9	4.9
0.8	0.9	1.0

--	--