

Yarn	10/1 Carded Weaving	20/1 Carded Hosiery	12/1 Combed Weaving	20/1 Combed Hosiery	30/1 Combed Weaving
Yarn	Siro	Normal	Normal	Compact	Compact
Cotton	Pak	CF	CF	CF	CF
Actual Count	10.1	20.05	12.1	20.05	30.4
Count CV %	1.02	1.02	1	1.03	1.1
Strength	257.5	110.5	227.3	128.5	85.6
Stren. CV %	3.8	3.9	3.75	3.9	3.9
CLSP	2601	2216	2750	2576	2602
RKM (UTJ-4)	18.8	16.4	18.8	18.5	19
U %	9.65	11.35	7.5	8.2	9.8
Thin -50 %	0	3	0	0	0.5
Thick +50 %	26	105	2.5	8	28
Neps +200 %	14	90	4.5	12	70
I P I	40	198	7	20	98.5
Haireness	9.8	6.7	7.7	5.3	4.6
sh	2.17	1.4	1.45	1.03	0.97

26/1 PV	36/1 PV	30/1 Acrylic	40/1 Acrylic
Normal	Normal	Normal	Compact
PV	PV	Acrylic	Acrylic
27.8	37.8	30.5	40.5
1.6	1.8	1.6	1.8
164.2	116.8	105	79
4.5	4.7	4.5	4.6
4565	4415	3203	3200
9.8	10.95	11.25	11.5
0	2	7	20
12	22	13	30
30	70	30	50
42	94	50	100
5.6	4.95	6.3	5.3
1.25	1.08	1.4	1.2