

TFO YARN SPECS				
YARN	20/2 CD WVG TPI = 7 ~ 8	20/2 CD WVG TPI = 13 ~ 14	24/2 CD WVG TPI = 7 ~ 8	30/2 CD WVG TPI = 16 ~ 17
YARN	Normal	Normal	Normal	Normal
COTTON	PAK	PAK	PAK	PAK
Actual Count	10.10 ~ 10.25	10.10 ~ 10.25	12.10 ~ 12.35	15.10 ~ 15.35
Count CV %	1.2~1.4	1.2~1.4	1.2~1.4	1.2~1.4
Strength	239.81	255	209.5	165
Stren. CV %	3.5~4.0	3.5~4.0	3.5~4.0	3.5~4.0
CLSP	2300 ~ 2450	2450 ~ 2600	2450 ~ 2600	2420 ~ 2580
RKM (UTJ-4)				
U %	7.75 ~ 9.00	9.0 ~ 9.8	9.0 ~ 9.8	9.0 ~ 9.8
Thin -50 %	0 ~ 1.0	0 ~ 1.0	0 ~ 1.0	0 ~ 1.0
Thick +50 %	8 ~ 20	8 ~ 25	10 ~ 30	10 ~ 35
Neps +200 %	8 ~ 20	8 ~ 20	10 ~ 25	15 ~ 35
I P I	16 ~ 40	16 ~ 45	20 ~ 56	25~ 71
Haireness	9.87	7.68	7.62	8.04

Note:

Yarn from out source